



*Garlock Style 7986
Premium Grade Neoprene Rubber Sheet*

Typical Physical Properties:

Material	Neoprene Rubber
Color	Black
Hardness, Shore A	60 +/-5
Tensile Strength, min.	2000 psi (14 MPa)
Elongation, min.	350%
Compression Set, max. ASTM Method B 70 hrs. @ 212°F (100°C) 25% Deflection	35%
Volume Change after Immersion in:	
ASTM #1 Oil 70 hrs. @ 212°F (100°C)	-4% to 3%
ASTM #3 Oil 70 hrs. @ 212°F (100°C)	50% to 80%
Thickness Available	1/16", 3/32", 1/8", 3/16", " and greater
Finish Available	Through 1/8" – Cloth Over 1/8" – Smooth
Temperature, max.	250°F (120°C)
Pressure, max.	250 psig
P x T, max.	50,000 psig x °F